weberad sec P

Integral waterproofing admixture in powder form

PRODUCT

weberad sec ${\bf P}$ is a waterproofing admixture in powder form, designed for use in all cement-based applications, such as:

- plastering and rendering exposed to rain
- mounting mortar
- joint grout
- screed
- concrete

It minimises penetration of moisture into the mortar. It improves the workability of fresh mortar, plaster, or concrete.

CHARACTERISTICS	
Appearance	White powder
Specific gravity	0.8
Solubility	Partial in water
Capillarity	3.2 g/dm².min½
Cl- content	NIL
weberad sec P is compatible with all portland cements.	

Capillarity at 28 days

	Capillarity
Control	6.75 g/dm².min½
Control	
+	3.2 g/dm².min½
weberad sec P	

INSTRUCTIONS FOR USE

weberad sec P is dosed for 1 kg of 50 kg cement:

- Spread the 1-kg over cement and aggregates. Usual mixture proportions shall be respected.
 Example for mortar: 1 part of cement for 3 parts of clean and selected sand. Do not pre- dissolve it in the mixing water.
- · Add the quantity of water required and mix well.
- Apply your mortar on a well-prepared substrate: clean, free from dust and all traces of oil or laitance.
 Few hours before apply, dampen the support.
- Cure and protect the mortar as usual.

PACKAGING

weberad sec ${\bf P}$ is supplied in 1 liter, 5 liters , 20 liters, 125 liters and 200 liters.

3 kg plastic bag (Only in UAE & Oman).

STORAGE

6 months from manufacturing date, in dry conditions and original packaging.

To be stored protected against frost. In case of frost, **weberad sec P** recovers its properties after progressive thawing.

SAFETY PRECAUTIONS

Avoid prolonged contact with skin. Wear protective gear for hands & eyes. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

