

Solvent free epoxy sealing primer

PRODUCT

weberfloor eposil plus is a high quality two-component epoxy primer designed to seal the porosity of the substrate thus providing a homogeneous and adherent surface to various epoxy and polyurethane coating systems. It can also be used as a bonding coat for epoxy mortars. It provides superior resistance of concrete to chemicals and daily abrasion, and reduces its absorption of water and salts.

SCOPE OF USE

- Parking decks
- Bridge decks
- Industrial floors
- Food industry flooring

CHARACTERISTICS

Color	Transparent
Solid content	100% by volume
Density	1.07
Pot life	1 hour at 30°C
Max over coating delay	1 day
VOC and formaldehyde content ISO/FDIS 11890-2/GC-MS	None (<10µg/l)

INSTRUCTIONS FOR USE

SURFACE PREPARATION

Careful surface preparation is essential for optimum finishing and durability.

Maximum moisture content should not exceed 5%.

New concrete structures need to dry for at least 28 days. Old coatings, dirt, fats, oils or organic substances need to be removed by a grinding machine. Possible surface irregularities need to be smoothed. Any loose surface pieces need to be thoroughly removed. The surface should then be roughened using a dust-free "grit-blasting" machine.

The substrate should be clean, dry and sound, free of any dust or contamination which may harmfully affect the adhesion of the primer layer.

WARNING: Do not wash surface with water!

PRODUCT PREPARATION

Mix the two parts for 2-3 minutes by an electric mixer with low rotation speed (< 300 rpm).

The epoxy must be well mixed to ensure proper chemical reaction. After mixing, apply immediately.

PRODUCT APPLICATION

weberfloor eposil plus is applied using a roller, brush or an airless sprayer.



PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
3.4 Kg	3.4 Kg	3.4 Kg	3.4 Kg	3.4 Kg	3.4 Kg	3.4 Kg	3.4 Kg
12 Kg	12 Kg	12 Kg	12 Kg	12 Kg	12 Kg	12 Kg	12 Kg

For very porous surfaces two coats may be required to seal effectively.

weberfloor eposil plus must be over coated within 24 hours. If it is not possible, aggregates 0.1-0.4 mm must be strewn on the wet applied **weberfloor eposil plus**.

CONSUMPTION

0.15 kg/m²

The concrete surface greatly affects coverage rate.

STORAGE

One year after manufacturing date in its original packing non open and in dry cool area.

SAFETY PRECAUTIONS

Application should be done in a ventilated area away from any heat source. Wear protective gear for hands and eyes and avoid breathing of vapor. If mixed resin comes into contact with the skin, it should be promptly removed before hardening, followed by thoroughly washing the skin with soap and water. In case of heavy vapor inhalation, place affected person in an open-air area. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting. In all cases, seek medical attention. In case of fire, use CO2 foam to extinguish. Tightly seal containers when not in use, store them away from heat and carefully dispose empty ones.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of weber. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

PG:22